

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	2.15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	1600	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	161	°C	ISO 11357-1/-3
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Film Extrusion

#### Delivery form

Powder

#### Features

Homopolymer

#### Regional Availability

Europe