

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1600	MPa	ISO 178
Thermal properties			
ASTM Data			
Melting Temperature	161	°C	ASTM D 3418
Other properties			
Density	905	kg/m ³	ISO 1183

Characteristics

Delivery form

Powder

Regional Availability

Europe

Features

Homopolymer