

**Product Texts**

Random copolymer with a high ethylene content.

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	4.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Flexural modulus, 23°C	700	MPa	ISO 178

**Thermal properties**

	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melting Temperature	134	°C	ASTM D 3418

**Other properties**

	Value	Unit	Test Standard
Density	895	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Powder

**Regional Availability**

Europe

**Features**

Copolymer, Random Copolymer