

**Product Texts**

Coextruded bioriented film.

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	7.3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	20	MPa	ISO 527
Flexural modulus, 23°C	620	MPa	ISO 178
Shore D hardness	58	-	ISO 7619-1

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	55	°C	ISO 75-1/-2
Vicat softening temperature, A	105	°C	ISO 306
<b>ASTM Data</b>			
Melting Temperature	131	°C	ASTM D 3418

**Other properties**

	Value	Unit	Test Standard
Density	895	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Film Extrusion

**Additives**

Antiblocking agent

**Features**

Heat Sealable

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Europe