

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	20	MPa	ISO 527
Flexural modulus, 23°C	620	MPa	ISO 178
Shore D hardness	58	-	ISO 7619-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	55	°C	ISO 75-1/-2
Vicat softening temperature, A	105	°C	ISO 306
<b>ASTM Data</b>			
Melting Temperature	131	°C	ASTM D 3418
<b>Other properties</b>			
Density	895	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Features

Heat Sealable

#### Regional Availability

Europe

#### Certifications

Food contact