

**Product Texts**

Random copolymer with a high ethylene content.  
Coextruded bioriented film.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	21	MPa	ISO 527
Flexural modulus, 23°C	700	MPa	ISO 178
Shore D hardness	62	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	60	°C	ISO 75-1/-2
Vicat softening temperature, A	120	°C	ISO 306
<b>ASTM Data</b>			
Melting Temperature	134	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	895	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Additives**

Antiblocking agent

**Regional Availability**

Europe

**Features**

Heat Sealable, Copolymer, Random Copolymer