

Product Texts

Propylene / alpha-olefin copolymer.
Coextruded bioriented film.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	350	MPa	ISO 178
Shore D hardness	53	-	ISO 7619-1
Thermal properties			
ASTM Data			
Melting Temperature	130	°C	ASTM D 3418
Processing Recommendation Extrusion			
Melt temperature	130	°C	-

Characteristics**Special Characteristics**

Transparent

Features

Heat Sealable, High Gloss, Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe