

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	650	MPa	ISO 178
Thermal properties			
ASTM Data			
Melting Temperature	131	°C	ASTM D 3418

Characteristics

Processing

Blown Film Extrusion, Film Extrusion

Additives

Antiblocking agent

Special Characteristics

Transparent

Features

Heat Sealable, High Gloss

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe