

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 9 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Flexural modulus, 23°C | 500 | MPa | ISO 178 |
| Thermal properties | | | |
| ASTM Data | | | |
| Melting Temperature | 128 | °C | ASTM D 3418 |

Characteristics

Processing

Blown Film Extrusion, Film Extrusion

Features

Heat Sealable, High Gloss

Special Characteristics

Transparent

Regional Availability

Europe