

**EMOPLN A 1550 UV**

PP

Emas Plastik San.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	15	g/10min	ISO 1133
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1600	MPa	ISO 527
Tensile Strength	20	MPa	ISO 527
Strain at break	15	%	ISO 527
Izod notched impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 180/1A
Shore D hardness	63	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	160	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	90	°C	ISO 75-1/-2
Vicat softening temperature, B	90	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	920	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Features**

Copolymer

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe, Near East/Africa