

**EP-N 31 MA**

PP

Petrochemical Commercial Co.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>100</b>	g/10min	ISO 1133
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>1500</b>	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>105</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>150</b>	°C	ISO 306
<b>Other properties</b>			
Density	<b>900</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Applications**

Packaging

**Regional Availability**

Europe, Asia Pacific, Near East/Africa