

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	7	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	20.3	MPa	ASTM D 638
Elongation at Yield	15	%	ASTM D 638
Gardner Impact	31.1	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	80.1	J/m	ASTM D 256

Characteristics

Processing

Injection Molding, Other Extrusion

Additives

Antiblocking agent

Features

Heat Sealable, Copolymer, Random Copolymer

Applications

General Purpose

Regional Availability

North America, Europe, South and Central America