

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	34.5	MPa	ASTM D 638
Elongation at Yield	9.8	%	ASTM D 638
Izod Impact notched, 1/8 in	32	J/m	ASTM D 256

### Characteristics

#### Processing

Injection Molding, Coating

#### Features

Gas Fading Resistance, Homopolymer

#### Applications

General Purpose

#### Regional Availability

North America, Europe, South and Central America