

ESENTTIA 35R80

PP

ESENTTIA

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	33	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.5	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Izod Impact notched, 1/8 in	45.4	J/m	ASTM D 256

Characteristics**Processing**

Injection Molding, Coating

Applications

General Purpose

Features

Soft Feel, Copolymer, Random Copolymer

Regional Availability

North America, Europe, South and Central America