

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	37	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	32.4	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256

Characteristics

Processing

Injection Molding, Other Extrusion, Coating

Features

Homopolymer

Applications

General Purpose

Regional Availability

North America, Europe, South and Central America