

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 60 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|-------|------|--------------------------|
| ASTM Data | | | |
| Tensile Strength at Yield | 24.8 | MPa | ASTM D 638 |
| Elongation at Yield | 5.2 | % | ASTM D 638 |
| Gardner Impact | 12.4 | J | ASTM D 2794,4226,5420 |
| Izod Impact notched, 1/8 in | 58.7 | J/m | ASTM D 256 |

Characteristics

Processing

Injection Molding

Additives

Release agent

Special Characteristics

High impact or impact modified

Features

Nucleated, Copolymer, Impact Copolymer

Applications

General Purpose

Regional Availability

North America, Europe, South and Central America