

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	30.3	MPa	ASTM D 638
Elongation at Yield	6.3	%	ASTM D 638
Rockwell Hardness	R 93	-	ASTM D 785
Izod Impact notched, 1/8 in	160	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	108	°C	ASTM D 648
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Additives

Antiblocking agent

### Special Characteristics

Anti-static

### Features

Copolymer, Impact Copolymer

### Chemical Resistance

Oxidation Resistance

### Certifications

Food contact, Food approval FDA 21 CFR

### Regional Availability

North America