

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	31	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Rockwell Hardness	R 83	-	ASTM D 785
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	98	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Blow Molding, Thermoforming

Special Characteristics

Anti-static, Transparent

Features

Copolymer, Random Copolymer

Chemical Resistance

Oxidation Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Medical

Regional Availability

North America