

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	150	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	150	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	147	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	147	°C	ASTM D 3418
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Special Characteristics

High impact or impact modified

#### Features

Copolymer

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa