

Product Texts

Medium melt flow rate homopolymer designed for high speed extrusion of woven fabrics exhibiting low water carry over.

Processing/Physical Characteristics**Value****Unit****Test Standard****ASTM Data**

Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Other properties**Value****Unit****Test Standard**

Density	900	kg/m ³	ASTM D 792
---------	------------	-------------------	------------

Characteristics**Processing**

Other Extrusion

Applications

General Purpose, Packaging

Delivery form

Pellets, Natural Color

Regional Availability

North America

Features

Homopolymer