

Product Texts

Premium polypropylene homopolymer resin for spunbond and fine denier fiber applications. Excellent uniformity for high-speed spinning of fine denier fibers.

Contains stabilizer package suitable for most nonwoven and filament products.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	36	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Delivery form

Pellets, Natural Color

Features

Homopolymer

Applications

Medical

Regional Availability

North America, South and Central America