

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	2.8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	36.8	MPa	ASTM D 638
Elongation at Yield	9	%	ASTM D 638
Izod Impact notched, 1/8 in	49.6	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	100	°C	ASTM D 648
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	15	%	ASTM D 1003
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Profile Extrusion, Sheet Extrusion, Other Extrusion, Blow Molding, Thermoforming

### Delivery form

Pellets, Natural Color

### Features

Homopolymer

### Applications

Packaging

### Regional Availability

North America