

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	50	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	20.4	MPa	ASTM D 638
Elongation at Yield	3.8	%	ASTM D 638
Gardner Impact	22.9	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	96.1	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Features

Blush Resistance/Low Crease Whitening, Thermal Stability, Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America