

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	34.4	MPa	ASTM D 638
Elongation at Yield	3.9	%	ASTM D 638
Izod Impact notched, 1/8 in	69.4	J/m	ASTM D 256
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding, Blow Molding

#### Delivery form

Pellets, Natural Color

#### Special Characteristics

High impact or impact modified

#### Features

High Crystallinity, Nucleated, Copolymer, Impact Copolymer

#### Regional Availability

North America