

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	22.4	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Gardner Impact	26.6	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	171	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	94.4	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

High impact or impact modified

Features

High Crystallinity, Nucleated, Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America