

Product Texts

Random copolymer grade primarily for non-oriented film applications. Contains slip additive and antiblock additive.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	7.3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.6	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Izod Impact notched, 1/8 in	51.2	J/m	ASTM D 256

Thermal properties

	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	72.2	°C	ASTM D 648

Other properties

	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets, Natural Color

Additives

Antiblocking agent

Features

Copolymer, Random Copolymer

Applications

Packaging

Regional Availability

North America