

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	6	g/10min	ISO 1133
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1500	MPa	ISO 527
Charpy notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	54	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Delivery form

Granules, Natural Color

#### Applications

Automotive

#### Features

Homopolymer

#### Regional Availability

Europe