

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	19	cm ³ /10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	15.1	MPa	ISO 527
Yield strain	4.3	%	ISO 527
Stress at break	11.6	MPa	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, +23°C	65	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	47	°C	ISO 75-1/-2
Other properties			
ISO Data			
Density	980	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Features

Ductile

Applications

Automotive

Regional Availability

Europe