

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	21	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	24	MPa	ISO 527
Yield strain	5.5	%	ISO 527
Stress at break	17	MPa	ISO 527
Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	48	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	78	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	910	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets, Black

### Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

### Features

Low Fogging, Low Odor

### Applications

Automotive

### Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa