

Formolene® 3335N

PP

Formosa Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	30.3	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Rockwell Hardness	R100	-	ASTM D 785
Izod Impact notched, 1/8 in	42.7	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

Packaging

Features

Copolymer, Random Copolymer

Regional Availability

North America

Certifications

Food contact, Food approval FDA 21 CFR