

**FORMPOLY PP3CUV**

PP

Formulated Polymers Limited

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>4</b>	g/10min	ASTM D 1238
Mold Shrinkage, MD	<b>0.0175</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>22</b>	MPa	ASTM D 638
Elongation at Break	<b>200</b>	%	ASTM D 638
Flexural Modulus	<b>1000</b>	MPa	ASTM D 790
Flexural Strength	<b>35</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>137</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>90</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>50</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>910</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Pellets

**Features**

Low Odor

**Additives**

Lubricants

**Applications**

Automotive, Electrical and Electronical

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Regional Availability**

Asia Pacific