

Gryfilen® C04-G

PP

Grupa Azoty S.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	28	MPa	ISO 527
Yield strain	6.5	%	ISO 527
Flexural modulus, 23°C	1420	MPa	ISO 178
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A

Characteristics**Delivery form**

Natural Color

Features

Copolymer, Impact Copolymer

Special Characteristics

High impact or impact modified

Regional Availability

Europe