

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	29	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	1510	MPa	ISO 178
Izod notched impact strength, +23°C	9	kJ/m ²	ISO 180/1A

Characteristics

Processing

Injection Molding, Other Extrusion, Compression Molding

Additives

Antiblocking agent

Features

Blush Resistance/Low Crease Whitening, Nucleated, Tribologic Grade, Copolymer, Impact Copolymer

Chemical Resistance

Environmental Stress Crack Resistance

Regional Availability

Europe