

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	50	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	35	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Izod notched impact strength, +23°C	2	kJ/m <sup>2</sup>	ISO 180/1A

## Characteristics

### Processing

Injection Molding

### Special Characteristics

Anti-static

### Features

Nucleated, Homopolymer

### Applications

Packaging

### Regional Availability

Europe