

Product Texts

TPO

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.4	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Yield stress	31	MPa	ISO 527
Yield strain	7	%	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Izod notched impact strength, +23°C	70	kJ/m ²	ISO 180/1A

Characteristics**Processing**

Pipe/Tube Extrusion

Features

Copolymer, Impact Copolymer

Delivery form

Natural Color

Regional Availability

Europe

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat