

**H01G-00**

PP

INEOS Olefins &amp; Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	1.2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	38	MPa	ASTM D 638
Elongation at Yield	9	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	99	°C	ASTM D 648

**Characteristics****Processing**

Injection Molding, Blow Molding

**Certifications**

Food contact, Food approval FDA 21 CFR

**Features**

Melt Strength, Homopolymer

**Regional Availability**

North America