

## H30S

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Melt flow index, MFI	35	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Yield stress	28.4	MPa	

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Regional Availability

Asia Pacific