

HD631CF

PP

Borouge

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1500	MPa	ISO 178
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	164	°C	ISO 11357-1/-3
Vicat softening temperature, A	154	°C	ISO 306
Optical properties			
ASTM Data			
Gloss	100	-	ASTM D 2457
Haze	2	%	ASTM D 1003
Other properties			
Density	905	kg/m ³	ASTM D 792
Film Properties			
ISO Data			
Tensile Modulus, parallel	1000	MPa	ISO 527-3
Dynamic coefficient of friction	0.3	-	ISO 8295
Type of extrusion	cast	-	-
Thickness of specimen	0.05	mm	-

Characteristics**Processing**

Film Extrusion

Applications

Packaging

Features

Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Certifications

Food contact