

HH10XT

PP

Polychim Industrie S.A.S.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	35	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Izod Impact notched, 1/8 in	39	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	103	°C	ASTM D 648
DTUL @ 264 psi	53	°C	ASTM D 648
Vicat Temperature	156	°C	ASTM D 1525
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Regional Availability

Europe

Features

Homopolymer