

**HNR100**

PP

Sasol Chemicals

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1550	MPa	ISO 527
Yield stress	34	MPa	ISO 527
Yield strain	8.5	%	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Charpy notched impact strength, +23°C	2.8	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	70	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	168	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	53	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
Vicat softening temperature, A	154	°C	ISO 306

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	220 - 280	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

Homopolymer

**Chemical Resistance**

Oxidation Resistance

**Certifications**

Food contact, Food approval FDA 21 CFR

**Regional Availability**

North America, Asia Pacific, Near East/Africa