

HP427J

PP

Braskem

Product Texts**Applications:**

BOPP Film

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	34	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Izod Impact notched, 1/8 in	35	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Characteristics**Features**

Homopolymer

Regional Availability

North America, Europe, South and Central America