

**HP501M**

PP

Rayomand Petroleum and Energy Commercial Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1500	MPa	ISO 527
Yield stress	34	MPa	ISO 527
Yield strain	9	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, +23°C	3.5	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	74	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
Vicat softening temperature, A	154	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Asia Pacific

**Features**

Homopolymer