

Haiplen EP80 Y2

PP

Taro Plast S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	35	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
ASTM Data			
Izod Impact notched, 1/8 in	40	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	70	°C	ISO 75-1/-2
Vicat softening temperature, A	138	°C	ISO 306
Vicat softening temperature, B	92	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1	mm	-
Limiting Oxygen Index	25	%	ASTM D 2863
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
Other properties			
Value			
Water absorption	0.05	%	Sim. to ISO 62
Density	1030	kg/m ³	ISO 1183

Characteristics**Delivery form**

Pellets

Special Characteristics

Flame retardant

Features

Laser Markable, Low Odor, Copolymer

Applications

Automotive, Electrical and Electronical

Regional Availability

Europe