

Hifax EPR 60/Bianco

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	20	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	900	MPa	ISO 178
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	160	°C	ISO 11357-1/-3
Vicat softening temperature, A	135	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Coating

Delivery form

Pellets, White

Special Characteristics

High impact or impact modified

Features

Good Adhesion, Thermal Stability, Copolymer

Applications

Building Construction

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa