

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	18	MPa	ISO 527
Flexural modulus, 23°C	1100	MPa	ISO 178
Izod notched impact strength, +23°C	45	kJ/m ²	ISO 180/1A
Izod notched impact strength	6	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	73	°C	ISO 75-1/-2
Vicat softening temperature, A	131	°C	ISO 306
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Copolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific, South and Central America