

**Hifax TKS 428P**

PP

LyondellBasell Industries

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	18	MPa	ISO 527
Flexural modulus, 23°C	1100	MPa	ISO 178

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Vicat softening temperature, A	131	°C	ISO 306

**Other properties**

	Value	Unit	Test Standard
Density	910	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Delivery form**

Pellets

**Applications**

Automotive

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe