

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	13	MPa	ISO 527
Flexural modulus, 23°C	550	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	60	°C	ISO 75-1/-2
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Features

Color Stability, Ductile, Scratch Resistant

Applications

Automotive

Regional Availability

Europe