

Hipolen P TA 41G

PP

Hipol a.d.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1300	MPa	ISO 527
Yield stress	32	MPa	ISO 527
Izod notched impact strength, +23°C	3.8	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Fiber Extrusion

Applications

Multifilament

Features

Color Stability, Homopolymer

Regional Availability

Europe