

Hipolen P TM 2G

PP

Hipol a.d.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1450	MPa	ISO 527
Yield stress	33	MPa	ISO 527
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	53	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	99	°C	ISO 75-1/-2
Vicat softening temperature, A	153	°C	ISO 306
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Features

Color Stability, Gas Fading Resistance, Homopolymer

Applications

Automotive, Medical, Multifilament, Packaging

Regional Availability

Europe