

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	19	MPa	ISO 527
Flexural modulus, 23°C	1100	MPa	ISO 178
Charpy notched impact strength, +23°C	45	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	40	kJ/m ²	ISO 180/1A
Izod notched impact strength	5	kJ/m ²	ISO 180/1A
Temperature	-40	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	80	°C	ISO 75-1/-2
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Features

Copolymer

Applications

Automotive

Regional Availability

Europe